

# 【受注対応表】 単位水量一定型15mm配合

2024/9/1  
大阪広域生コンクリート協同組合

普通コンクリート (AE減水剤単位水量一定型配合)							
セメント (材齢)	骨材最大寸法		15 mm				
	単位水量(kg/m <sup>3</sup> )		180	185	190	200	210
	呼び強度	スランプ W/C	8	12	15	18	21
N (28)	18	68	●	●	●	●	—
	21	63	●	●	●	●	●
	24	57	●	●	●	●	●
	27	53	●	●	●	—	—
	30	49	●	●	●	—	—
BB (28)	18	66	●	●	●	●	—
	21	61	●	●	●	●	●
	24	55	●	●	●	●	●
	27	51	●	●	●	—	—
	30	47	●	●	●	—	—
H (7)	18	62	●	●	●	●	—
	21	58	●	●	●	●	●
	24	53	●	●	●	●	●
	27	49	●	●	—	—	—
	30	46	●	●	—	—	—
H (置換え)	18	68	●	●	●	●	—
	21	63	●	●	●	●	●
	24	57	●	●	●	●	●
	27	53	●	●	—	—	—
	30	49	●	●	—	—	—

●: JIS外対応, —: 受注不可  
注) 単位水量の減水は対応できません。

普通コンクリート (高性能AE減水剤単位水量一定型配合)								
セメント (材齢)	骨材最大寸法		15 mm					
	単位水量(kg/m <sup>3</sup> )		175	180	185	190	195	195
	呼び強度	スランプ W/C	8	12	15	18	21	23
N (28)	27	54	—	●	●	●	●	—
	30	50	—	●	●	●	●	—
	33	47	●	●	●	●	●	●
	36	44	●	●	●	●	●	●
	39	41	●	●	●	●	●	●
	40	40	●	●	●	●	●	●
	42	38	●	●	●	●	●	●
	45	36	●	●	●	●	●	●
BB (28)	27	52	—	●	●	●	●	—
	30	48	—	●	●	●	●	—
	33	46	●	●	●	●	●	●
	36	43	●	●	●	●	●	●
	39	40	●	●	●	●	●	●
	40	39	●	●	●	●	●	●
	42	37	●	●	●	●	●	●
	45	35	●	●	●	●	●	●
H (7)	27	51	—	●	●	●	●	—
	30	47	●	●	●	●	●	●
	33	43	●	●	●	●	●	●
	36	40	●	●	●	●	●	●
	39	38	●	●	●	●	●	●
	40	37	●	●	●	●	●	●
H (置換え)	27	54	—	●	●	●	●	—
	30	50	●	●	●	●	●	—
	33	47	●	●	●	●	●	●
	36	44	●	●	●	●	●	●
	39	41	●	●	●	●	●	●
	40	40	●	●	●	●	●	●
	42	38	●	●	●	●	●	●
	45	36	●	●	●	●	●	●

●: JIS外対応, —: 受注不可  
注) 単位水量の減水指定は対応可能ですが別途見積りとなります。