

# 【受注対応表】 AE減水剤配合(旧配合)

2024/9/1

大阪広域生コンクリート協同組合

普通コンクリート (AE減水剤 旧配合)											
セメント (材齢)	骨材最大寸法		20 mm					40 mm			
	呼び強度	スランプ W/C	8	12	15	18	21	5	8	12	15
N (28)	18	68	○	○	○	○	-	○	○	○	○
	21	63	○	○	○	○	○	○	○	○	○
	24	57	○	○	○	○	○	○	○	○	○
	27	53	○	○	○	○	○	○	○	○	○
	30	49	○	○	○	○	○	○	○	○	○
BB (28)	18	66	○	○	○	○	-	○	○	○	○
	21	61	○	○	○	○	○	○	○	○	○
	24	55	○	○	○	○	○	○	○	○	○
	27	51	○	○	○	○	○	○	○	○	○
	30	47	○	○	○	○	○	○	○	○	○
	33	43	●	●	●	●	●	-	-	-	-
BB (56)	18	(70)	★	★	★	★	-	★	★	★	★
	21	64	○	○	○	○	○	○	○	○	○
	24	58	○	○	○	○	○	○	○	○	○
	27	53	○	○	○	○	○	○	○	○	○
	30	49	○	○	○	○	○	○	○	○	○
	33	46	○	○	○	○	○	-	-	-	-
BB (91)	21	68	○	○	○	○	○	○	○	○	○
	24	61	○	○	○	○	○	○	○	○	○
	27	56	○	○	○	○	○	○	○	○	○
	30	51	○	○	○	○	○	○	○	○	○
	33	48	○	○	○	○	○	-	-	-	-
H (7)	18	62	○	○	○	○	-	○	○	○	○
	21	58	○	○	○	○	○	○	○	○	○
	24	53	○	○	○	○	○	○	○	○	○
	27	49	○	○	○	○	○	○	○	○	○
	30	46	○	○	○	○	○	○	○	○	○
H (置換え)	18	68	●	●	●	●	-	●	●	●	●
	21	63	●	●	●	●	●	●	●	●	●
	24	57	●	●	●	●	●	●	●	●	●
	27	53	●	●	●	●	●	●	●	●	●
	30	49	●	●	●	●	●	●	●	●	●

○:JIS対応, ●:JIS外対応, ★:JIS外対応(配合計算書無添付), -:受注不可