

【受注対応表】 高性能AE減水剤配合

2024/9/1

大阪広域生コンクリート協同組合

普通コンクリート（高性能AE減水剤配合）												
セメント (材齢)	骨材最大寸法		20 mm									
	スランブ		8	12	15		18		21			23
	呼び強度	W W/C	165	170	170	175*	175	180*	175	180	185**	185
N (28)	24	57	—	—	—	○	○	○	—	○	○	—
	27	54	—	○	●	○	○	○	—	○	○	—
	30	50	—	○	●	○	○	○	●	○	○	—
	33	47	○	○	●	○	○	○	●	○	○	●
	36	44	○	○	●	○	○	○	●	○	○	●
	39	41	●	●	●	●	●	●	●	●	●	●
	40	40	○	○	●	○	○	○	●	○	○	●
BB (28)	24	55	—	○	—	○	○	○	—	○	○	—
	27	52	—	○	●	○	○	○	—	○	○	—
	30	48	—	○	●	○	○	○	●	○	○	—
	33	46	○	○	●	○	○	○	●	○	○	●
	36	43	○	○	●	○	○	○	●	○	○	●
	39	40	●	●	●	●	●	●	●	●	●	●
	40	39	○	○	●	○	○	○	●	○	○	●
BB (56)	24	57	—	●	—	●	●	●	—	●	●	—
	27	54	—	○	●	○	○	○	—	○	○	—
	30	50	—	○	●	○	○	○	●	○	○	—
	33	48	—	○	●	○	○	○	●	○	○	—
	36	44	○	○	●	○	○	○	●	○	○	●
	39	41	●	●	●	●	●	●	●	●	●	●
	40	40	○	○	●	○	○	○	●	○	○	●
BB (91)	24	—	—	—	—	—	—	—	—	—	—	—
	27	57	—	●	—	●	●	●	—	●	●	—
	30	52	—	●	●	●	●	●	—	●	●	—
	33	50	—	●	●	●	●	●	—	●	●	—
	36	46	●	●	●	●	●	●	●	●	●	●
	39	43	●	●	●	●	●	●	●	●	●	●
	40	42	●	●	●	●	●	●	●	●	●	●
H (7)	24	54	—	○	—	○	○	○	—	○	○	—
	27	51	—	○	—	○	○	○	—	○	○	—
	30	47	○	○	—	○	○	○	●	○	○	●
	33	43	○	○	—	○	○	○	●	○	○	●
	36	40	○	○	—	○	○	○	●	○	○	●
	39	38	●	●	—	●	●	●	●	●	●	●
H (28)	24	57	—	—	—	●	●	●	—	●	●	—
	27	54	—	●	—	●	●	●	—	●	●	—
	30	50	●	●	—	●	●	●	●	●	●	—
	33	47	●	●	—	●	●	●	●	●	●	●
	36	44	●	●	—	●	●	●	●	●	●	●
	39	41	●	●	—	●	●	●	●	●	●	●
	40	40	●	●	—	●	●	●	●	●	●	●
L (56)	24	—	—	—	—	—	—	—	—	—	—	—
	27	58	—	—	—	—	—	○	—	○	○	—
	30	54	—	○	—	○	○	○	—	○	○	—
	33	51	—	○	—	○	○	○	●	○	○	—
	36	48	—	○	—	○	○	○	●	○	○	—
	39	45	—	●	—	●	●	●	●	●	●	—
	40	45	—	○	—	○	○	○	●	○	○	—
L (91)	24	—	—	—	—	—	—	—	—	—	—	—
	27	—	—	—	—	—	—	—	—	—	—	—
	30	58	—	—	—	—	—	●	—	●	●	—
	33	55	—	●	—	●	●	●	—	●	●	—
	36	52	—	●	—	●	●	●	●	●	●	—
	39	49	—	●	—	●	●	●	●	●	●	—
	40	48	—	●	—	●	●	●	●	●	●	—

○:JIS対応, ●:JIS外対応, —:受注不可

※:基準水量

※標準空気量は4.5%です。上表で全てJIS表示外品となりますが、空気量2.0, 2.5, 3.0, 3.5, 4.0, 5.0%に対応します。